



PRODUCT SPECIFICATION

SPECIFICATION

Product Name

TAM SENTETİK METAL İŞLEME VE SOĞUTMA SIVISI METAL WORKING FLUID FULLY SYNTHETIC

PRIMARY TESTS	METHOD	SPECIFICATION		
		MİN	TYP	MAX
Appearance	Visual		Clear and Bright	
Emulsion Appearance	Visual		Transparent	
Density 15'C, g/ml	ASTM D4052 / TS EN ISO 12185	1,02	1,05	1,135
Emulsion PH, 20'C	TS 4614	8.5	9	

SECONDARY TESTS	METHOD	SPECIFICATION		
		MİN	TYP	MAX
Rust Test % (stained area)	TS 5208			3
Low and High Temperature Stability	TS 11299			Turbidity, sedimentation, gelation, phase separation should not be seen.

Usage : Used between %2 - %5 oil and between %98 -%95 water, mixed until a clear mixture is obtained.
Refractometer Factor : 2,32

* As the defined values are typical values, there can be some little changes according to the production. M Oil keeps all the rights to update and change the formulations of products without making any announcements. For the updated informations and technical datas about the products and product packagings, please contact with M Oil.