



# PRODUCT SPECIFICATION

# SPECIFICATION

**Product Name: DIZEL SUPER EKSTRA HD 10W**

PRIMARY TESTS	METHOD	SPECIFICATION		
		MIN	TYP	MAX
Appearance	Visual		Clear and Bright	
Colour	ASTM D1500 / TS 1713 ISO 2049	0.5	1	3
Density 15 °C, g/ml	ASTM D4052 / TS EN ISO 12185	0.860	0.880	0.895
Kinematic Viscosity 100 °C, mm <sup>2</sup> /s	ASTM D445 / TS EN ISO 3104	5	6.5	8.5
Kinematic Viscosity 40 °C, mm <sup>2</sup> /s	ASTM D445 / TS EN ISO 3104		40	
Viscosity Index	ASTM D2270 / TS ISO 2909		104	
T.B.N. mgKOH/g	ASTM D2896 / TS ISO 3771	10		
Cold Cracking (-25 °C), cp	ASTM D5293 / TS 1896			7000

SECONDARY TESTS	METHOD	SPECIFICATION		
Pour Point, °C	ASTM D97 / TS EN ISO 3016			- 30
Flash Point, °C (COC)	ASTM D92 / TS EN ISO 2592	202		
Aniline Point, °C	TS 1615 ISO 2977	90		
Evaporation Loss, %m/m	ASTM D5800 / TS 13489			15
Predicting the Borderline Pump. Temp. °C (-30 °C) TS 4409				60000
Foaming Characteristic (II Kd.) ml/ml	ASTM D892 / TS 1834 ISO 6247			50/0
Sulfated Ash %m/m	ASTM D874 / TS ISO 3987			3
Copper Corrossion (100 °C, 3 hours)	ASTM D130 / TS 2741 EN ISO 2160			1b

**PERFORMANCE LEVELS: API : CF 4 / SG ACEA E2, MB 227.1, MB 228.0, MAN 270, MTU Type1, JASO MA, Allison C3, CAT TO 2, MIL-L-2104D**

Document Code	Revision No/Date	Page No	Prepared	Checked	Approved
KG-ÜS-108	09/16.10.2023	1/1	FACTORY HSEQ & LAB. MANAGER	MANAGEMENT REPRESENTATIVE	FACTORY MANAGER

\* As the defined values are typical values, there can be some little changes according to the production. M Oil keeps all the rights to update and change the formulations of products without making any announcements. For the updated informations and technical data about the products and product packagings, please contact with M Oil.